



Graver Technologies

Quality Department

ECODEX[®]
MERIDIAN[™] M2000
HYDROGEN/HYDROXIDE
FORMS

SPEC NO	GTS-ME-2000
REV NO	1
DATE	May 9, 2001
QA APPROVAL	<i>Keith Platoff</i>

PROPERTIES

SPECIFICATIONS

Resin Type	Strongly Acidic Cation Exchange Resin Strongly Basic Anion Exchange Resin
Functionality	Sulfonic Acid Quaternary Ammonium
Matrix	Styrene-Divinylbenzene
Cation: Anion Ratio	1:1 Equivalents
Total Moisture	73% (max)
Total Exchange Capacity	4.8 meq/dry g (Cation) (min) 4 meq/dry g (Anion) (min)
Percent of Sites	99% Hydrogen (min) 95% Hydroxide (min) 1% Chloride (max)
Settled Volume/ Turbidity	55% (V/V) (min) 15 NTU (max)
Metals (mg/dry kg)	100 Sodium (max) 50 Aluminum (max) 50 Iron (max) 10 Copper (max)