



Graver Technologies

Quality Department

**GRAVEX®
GR 1-1 US
HYDROXIDE FORM**

SPEC NO	GTS-11-US
REV NO	0
DATE	June 12, 2001
QA APPROVAL	<i>Keith Platoff</i>

PROPERTIES

Resin Type

Functionality

Matrix

Total Exchange Capacity

Water Retention

Percent of Sites

Particle Size

Friability

Whole Uncracked Beads

Metals (mg/dry kg)

Shipping Weight

SPECIFICATIONS

Strongly Basic Type I Anion Exchange Resin

Quaternary Ammonium

Styrene-Divinylbenzene

1 meq/mL (min)

50 - 60% Cl⁻ Form

97% Hydroxide (min)

0.5% Chloride (max)

610 +/- 50 μm Mean Size

350 g average (min)

95% > 200 g (min)

95% (min)

50 Sodium (max)

50 Iron (max)

10 Copper (max)

50 Aluminum (max)

40 lbs/ft³ (641 g/L)